

AMENDMENTS TO THE CLAIMS

1. (Currently amended) A method of surface treatment of a titanium metal ~~wherein~~ comprising

_____plasma carburizing ~~is carried out~~ in an atmosphere comprising a carburizing gas having ~~the a~~ molar ratio of hydrogen atoms (H) to carbon atoms (C) adjusted to $1 \leq H/C \leq 9$ at a pressure of 13-400 Pa and a temperature of 400-690 °C.

2. (Currently amended) A method of surface treatment of a titanium metal comprising the ~~steps of~~ heating the titanium metal to a temperature of 400-690 °C in a cleaning gas atmosphere containing hydrogen gas,

_____subjecting the surface of the titanium metal to cleaning by applying a DC voltage of 200-1500 V, and

_____plasma carburizing in an atmosphere comprising a carburizing gas having ~~the a~~ molar ratio of hydrogen atoms (H) to carbon atoms (C) adjusted to $1 \leq H/C \leq 9$ at a pressure of 13-400 Pa and a temperature of 400-690 °C.